



Shadow Gap Cladding Technical Specification

PIRANHA TAKES CARE OF IT!

Talasey Ltd are FSC® certified and by choosing Piranha you are helping take care of the world's forests

For more information visit www.piranhadecking.co.uk



intertek




SHADOW GAP CLADDING

TECHNICAL SPECIFICATION

Test Item	Test Method	Pass Requirements	Cladding
Flexural Properties Maximum Load	EN 15534-1 ANNEX A EN 15534-4 Table 3	F'MAX \geq 3300N (Mean)	Mean 6032N
		F'MAX \geq 3000N (Min)	Min 5817N
Flexural Properties Deflection	EN 15534-1 ANNEX A EN 15534-4 Table 3	Deflection under a load of 500N	
		Mean \leq 2.0mm	Mean 0.31mm
		MAX \leq 2.5mm	Max 0.32mm
Impact Strength	EN 15534-1 7.1.2.1	Pass	No Crack
Bending Strength	EN 15534-1 7.5	N/A	37.6Mpa
Falling Mass Impact Resistance	EN 15534-1 Section 7.1.2.1	None of 10 test specimens shall show a failure with a crack length \geq 10mm or a depth of residual indentation \geq 0.5mm	Max crack length: No Crack Appeared Max. Residual Indentation: 0.21mm
Water Absorption Boiling Test	EN 15534-1 8.3.3	Mean \leq 7%	Mean \leq 0.85%
		Individual \leq 9%	Individual \leq 0.90%
Fire	EN ISO 9239-1:2002 EN ISO 11925-2:2002 Exposure = 30s	In accordance with EN 13501-1	Class: E
Swelling after boiling test	EN 15534-1 8.3.3	N/A	Mean Swelling: 0.82% in Thickness 0.10% in Width 0.10% in Length Max. Swelling: 0.93% in Thickness 0.14% in Width 0.14% in Length
Modulus of Elasticity	EN 15534-1 7.5	N/A	3.30Gpa

Dimensions:
170x26x3600mm
Working Height:
150mm



Carbon Black



Brown Cedar



Antique Grey