



Terrafuzion

Technical Specification

PIRANHA TAKES CARE OF IT!

Talasey Ltd are FSC® certified and by choosing Piranha you are helping take care of the world's forests
For more information visit www.piranhadecking.co.uk



intertek




TERRAFUZION

TECHNICAL SPECIFICATION




Test Item	Test Method	Pass Requirements	TerraFuzion
Flexural Properties Loading	EN 15534-1 ANNEX A EN 15534-4 Table 3	$F'_{MAX} \geq 3300N$ (Mean)	Mean 4500N
		$F'_{MAX} \geq 3000N$ (Min)	Min 4000N
Flexural Properties Deflection	EN 15534-1 ANNEX A EN 15534-4 Table 3	Deflection under a load of 500N	
		Mean $\leq 2.0mm$	Mean 1.16mm
		MAX $\leq 2.5mm$	Max 1.30mm
Impact Strength	EN 15534-1 6.6.4	Pass	No Crack Indentation $\geq 0.03mm$
Tensile Strength	EN 15534-1 7.5	N/A	19.0Mpa
Slip Resistance	EN ISO 15534-1-6.4.2 CEN/TS 15676:2007	≥ 36	Wet L 50
		≥ 36	Wet H 65
		≥ 36	Dry L 88
		≥ 36	Dry H 96
Water Absorption	EN 15534-1 8.3.3	Mean $\leq 7\%$	Mean $\leq 0.73\%$
		Individual $\leq 9\%$	Individual $\leq 0.73\%$
Fire	EN ISO 9239-1:2002 EN ISO 11925-2:2002 Exposure = 15s	In accordance with EN 13501-1	Class: B Smoke: S1
Linear Mass	EN 15534-1 6.5 Method A	N/A	Mean 3130g/M
			Min 3129g/M


Dimensions:
140x23x3600mm



Mocha / Espresso



Sandstone / Island Mist



Slate / Graphite